

S5 1 PN='SU 313839'  
? t5/7/1

5/7/1  
DIALOG(R)File 350:Derwent WPIX  
(c) 2003 Thomson Derwent. All rts. reserv.

000879921

WPI Acc No: 1972-39909T/197225

Solid paint mixes - addition of gypsum to improve finish

Patent Assignee: RIGA CHEMICAL WORKS (RIG -N)

Number of Countries: 001 Number of Patents: 001

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
SU 313839	A					197225 B

Priority Applications (No Type Date): SU 1404051 A 19700209

Abstract (Basic): SU 313839 A

Paint mixes which after dilution with water and addition of  
painters glue provide protective and decorative finish comprise (in %  
wt) 0.6-20 pigment, 5-6 kaolin and 74-94 partially calcined gypsum.

Derwent Class: G02

International Patent Class (Additional): C09D-003/06

?

Union of the Soviet Socialist Republics

State Committee of the USSR on Inventions and Discoveries

**SPECIFICATION**

**attached to Author's Certificate**

(11)

**313839**

(51)

Int. Cl. C 09d 3/06

Su

(61) Additional to the Author's Certificate: -

(22) Filed on November 09, 1970 (21) 1404051/29-33

(UDK) 691.57 (088.8)

with an additional application No. -

(23) Priority -

Published on September 07, 1971, Bulletin No. 27

The Specification is published on November 17, 1971

(72) Authors of the Invention Girshovich, Kh, I.

(71) Applicant Rizhski Kchemical Plant

**(54) DRY PAINT FOR INTERNAL FINISHING OF SURFACES OF BUILDINGS AND STRUCTURES**

The present invention relates to dry paints for internal finishing of plastered, brick, concrete, and wallpapered (old wallpaper) surfaces of homes, industrial buildings and public structures.

A dry paint for internal finishing of surfaces of buildings and structures is known, this paint containing a pigment and a mineral filler.

The object of the present invention is to improve the painting and decorative properties of the paint.

This object is attained by the paint containing as a filler a mixture of powdered kaolin and partially calcined gypsum with the content of gypsum hemihydrate of 1-20%, with the content ratio of components being as follows, wt. %:

Pigment	0.6-20
Filler:	
kaolin	5-6
partially calcined gypsum	74-94

After diluting with water and adding a painting glue, the paint has improved adhesion to the surface because  $\text{CaSO}_4 \cdot \frac{1}{2}\text{H}_2\text{O}$  is converted into  $\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$  on the painted surface. At the same time, because the content ratio of  $\text{CaSO}_4 \cdot \frac{1}{2}\text{H}_2\text{O}$  in the paint is no more than 18%, the painting properties of the paint are improved. When the content ratio of  $\text{CaSO}_4 \cdot \frac{1}{2}\text{H}_2\text{O}$  is above this level, the painting properties are degraded.

The dry paint effectively fills pores and recesses on the surface painted.

### Patent Claim

A dry paint for internal finishing of the surface of buildings and structures, comprising a pigment and a mineral filler, *characterized* in that, with the object of improving painting and decorative properties of the paint, it contains as a filler a mixture of powdered kaolin and partially calcined gypsum with the content of gypsum hemihydrate of 1-20%, with the content ratio of components being as follows, wt.%:

Pigment	0.6-20
Filler:	
kaolin	5-6
partially calcined gypsum	74-94

Translated from Japanese by:  
Michael J. Sidor & Co., Inc.  
527 S. Mitchell Ave.  
Arlington Heights, IL 60005  
(847) 259-7697  
File No.: MS4997